



Test Report

No: GZFDO109400995FD-1

Date: Apr. 15, 2011

Client name : BestSub Technologies Co., Ltd
Client address: Rm 810 Exchange Square, No.268 Dongfeng Zhong Road, Yuexiu District,
Guangzhou, 510030, China.

The following sample(s) was/were submitted by/ on behalf of the client as:

Sample Name: 11OZ FOOTBALL MUG
Batch/Date: /
Manufacturer: BestSub Technologies Co., Ltd
Item no.: B11ZQ
SGS reference no.: GZ1004032042/CHEM
SGS job no.: GZFDO109400995FD-1
Date of receipt: Apr. 01, 2011
Testing period: Apr. 01, 2011 ~ Apr. 13, 2011

TEST(S) REQUESTED:

Selected test(s) as requested by applicant:
As specified by client, with reference to European Council Directive 84/500/EEC & 2005/31/EC – Ceramic articles intended to come into contact with foodstuffs requirements on lead and cadmium extracted by acetic acid from ceramic surfaces.

TEST METHOD(S):

As specified in EEC Directive 84/500/EEC & 2005/31/EC and EN1388:1996.
Analysis was performed by Inductively Coupled Plasma Atomic Emission Spectrometer (ICP-AES).

TEST RESULT(S):

Please refer to next page.

CONCLUSION:

When tested as specified, the submitted sample(s) comply with European Council Directive 84/500/EEC & 2005/31/EC requirements on lead and cadmium extracted by acetic acid from ceramic surfaces.

Signed for and on behalf of SGS

Authorized Signature

Test Report

No: GZFD0109400995FD-1

Date: Apr. 15, 2011

TEST RESULT(S):

Leachable Lead and Cadmium Content

Category 2

PASS

No	Depth (mm)	Diameter (mm)	Extract Volume (ml)	Lead (mg/L)	Cadmium (mg/L)
1	85	77	350	< 0.05	< 0.01
2	85	77	350	< 0.05	< 0.01
3	85	77	350	< 0.05	< 0.01
4	85	77	350	< 0.05	< 0.01
-	-	-	Limit	4.0	0.3

Lip and rim area

PASS

No	Depth (mm)	Diameter (mm)	Internal Volume (ml)	Extract Volume (ml)	Lead (mg/article)	Cadmium (mg/article)
1	85	77	350	220	< 0.05	< 0.01
2	85	77	350	220	< 0.05	< 0.01
3	85	77	350	220	< 0.05	< 0.01
4	85	77	350	220	< 0.05	< 0.01
-	-	-	-	Limit	2.0	0.2

All results were read directly from ICP.

Remark: 1. < = Less than

2. Category 1


Articles which cannot be filled and articles which can be filled, the internal depth of which does not exceed 25mm.

Category 2

All other articles which can be filled.

Category 3

Cooking ware; packaging and storage vessels having a capacity of more than three litres.




Test Report

No: GZFD0109400995FD-1

Date: Apr. 15, 2011

SAMPLE DESCRIPTION: Ceramic cup

Photo Appendix



SGS authenticate the photo on original report only
*** End of Report***